

APFLOOR SLUL

Solvent-free low viscous Self Leveling Epoxy Screed.

Description

A low viscous version from the APFLOOR range of SCREED, APFLOOR SLUL is a solvent free, epoxy polyamido-amine based, two component, all- purpose epoxy system recommended for concrete and masonry substrates. Being a low viscous, APFLOOR SLUL with its special blend of surfactants, penetrates easily and efficiently into the porosities and capillaries of the concrete substrate forming a very strong bond with the substrate. APFLOOR SLUL is based on a polyamido-amine cured epoxychemistry and has excellent bond strength with the substrate With excellent Self levelling property. It can also be used as a sealer and a self levelling screed with the aid of graded aggregates such as FQ 80, FQ 200, FQ 250 and FQ 300 for various screed thicknesses



Uses

APFLOOR SLUL is used as self levelling screed and sealer coat in conjunction with APFLOOR and APCRETE range of floor toppings. It is also used a water-wipeablegrout for kota stones, with the aid of aggregates and EPI colourants.

Key features

- Excellent bond strength and self levelling, with concrete failure inpull-off test
- Low viscous
- Slow curing
- Bonds tenaciously to become an integral part of the floor

Properties

Type	: Epoxy- polyamidoamine
Colour	: Brownish yellow
Pot life @ 27°C ASTM D 2471	: ≥ 90 minutes
Drying time : screed ASTM D 1640	
Surface dry	: ≥ 50 minutes
Tack free dry	: ≥ 5 hrs
Hard dry	: ≥ 24 hrs

Mixing ratio Resin to Hardener	: 2 : 1 by volume
Density of the mix screed (Liquid : Aggregate) 1 : 2.5	: 1.76 gm / cc
Application	: By roller / brush
Overcoat interval	
Over primer application	: Maximum 24 hours
Over screed application	: Maximum 7 days
Shelf life	: 12 months in the unopened container
Recommended thinner	: PUT 502 (Clean up)

Performance data

The mandatory performance parameters as per FeFRA and EFNARC guidelines for resin flooring system

Pull of adhesion test ASTM D 7234-2022	: ≥ 2 MPa for M20 grade concrete or
---	--

Other mechanical properties

Tensile strength : screed ASTM D 638	: 8 MPa
---	---------

Concrete failure

Flexural strength : screed : 12 MPa
ASTM D 790

Note : The typical physical properties given above are derived from testing in a controlled laboratory environment. Results derived from testing field-applied samples may vary, dependent on actual site conditions

Directions to use

Surface preparation : The long-term durability of the applied APFLOOR SLUL coating is dependent upon the adhesive bond achieved between the flooring material and substrate. It is most important therefore, that substrate surfaces are correctly prepared prior to application. Ensure that the residual moisture level in the concrete is below 5%. All substrates should be sound and free from contamination such as mortar and paint splashes, curing compound residue, oil, or grease. Excessive laitance should be removed by light mechanical scrubbing, grinding or grit blasting. Oil and grease contamination must be completely removed by grinding down to sound, clean concrete. Alternatively, blasting techniques can be used to provide the required substrate.

Priming

APFLOOR EP 15 Resin and APFLOOR EP 15 Hardener is supplied separately in 20 lts packing. Mix Resin and Hardener in proportion of 2:1 by volume. Solvent or thinners should not be added. A forced action mixer with a paddle fitted into a heavy duty, slow speed electric hand drill is recommended for mixing. The material is poured onto the prepared substrate and spread to the required thickness with a roller. Allow to cure overnight. Porous floors may require two coats of primer. Overcoating window time should not exceed 24 hours. In case overcoating window exceeds 24 hours, recoating of primer is necessary.

Screed

Mix Resin and Hardener in proportion of 2:1 by volume, and add formulated aggregates like FQ 200 in recommended ratio as per the screed thickness. Solvent or thinners should not be added. A forced action mixer with a paddle fitted into a heavy duty, slow speed electric hand drill is recommended for mixing. The material is poured onto the primed substrate and spread to the required thickness. Allow to cure overnight. In case over coating window exceeds 48 hours, light mechanical abrading to be done on the screed surface before overlaying with subsequent topping. If the over coating window on top of screed exceeds 7 days, light abrading the screed surface and priming is essential..

Packaging & Theoretical coverage

:

APFLOOR	:	Pre-weighed set of 16/18/20/24. KG	:	1 set cover 10 sqm @ 1mm/ 6 sqm @ 2mm / 4
SLUL				sqm @3mm / 3 sqm @4mm
(Screed)				

Storage and handling

The product should be stored in accordance with national regulations. It should be kept in a cool, well ventilated area, away from heat, direct sunlight, sparks and children. Handle with care. Mix resin and hardener as per the ratio. Use the mix solution within the pot life time.

Health and safety precautions

Please refer to MSDS. Observe reasonable care and employ ordinary hygienic principles such as washing the hands with soap and water before eating or smoking. It is recommended to wear gloves, goggles and nose masks while application. In case of splashes on the skin, dampen the cloth with thinner PUT 503 and wipe the hands with the cloth. Wash then with soap and water. Dried film is non toxic. In case of contact with eyes, rinse with plenty of water and seek medical advice. In case of continuous exposure to vapours, the applicator should be immediately moved to get fresh air. The disposal of excess or waste material should be carried out in accordance with the local legislations.

Limitations

It is not compatible for application over asphalt, unmodified sand-cement screeds or PVC tiles and sheets. APFLOOR SLUL coating laid floor will be scratched due to nails or sharp objects protruding from machinery, packings, or trolleys moving on the floor. Presence of sand will also cause abrasion. The product is not advised to be applied below 15°C as the flow reduces. While applying the product above 35°C, there can be a problem of low pot life etc., and it will be difficult to apply the material. Cured product is not suitable for exposure to sub-zero temperatures and above 65°C.

